

AGEPAN® SYSTEM

...works
harder!

Please observe the processing instructions on the back!
Følg venligst monteringsvejledningen på bagsiden!

AGEPAN® UDP T+G

THE SOLID SARKING BOARD
DET STABILE UNDERTAG

info@agepan.de

www.sonaeaurauco.com/agepan

SONAE
RAUCO
Taking wood further

AGEPAN® SYSTEM

...works harder!

AGEPAN® UDP T+G – THE SOLID SARKING BOARD

General short processing instructions



STORAGE AND TRANSPORT

- Boards must be stored horizontally
- Distance of the wooden supports must not exceed 60 cm
- Edges should be protected against damage
- Individual boards have to be transported in an upright position, if possible
- When destacking, the full board thickness has to be taken



OUTDOOR EXPOSURE

- When using as under-roof board, storage under natural weathering conditions is possible to a limited extent of up to eight weeks
- Moisture absorption reduces the strength of the board and will not be fully restored even after drying
- Temporary covering with sheets may be useful here, especially if subsequent works are done after a delay
- If the boards have absorbed moisture, re-drying to the required moisture has to be ensured before finishing the component
- Possible changes in the board length have to be considered regarding the design parameters
- The counter-battens must be fastened at all events and the sealing and masking have to be rainproof and windproof
- Draining surface water can cause discolouration in sheet metal panelling, therefore use suitable protective films and only remove them after the roof has been completely covered



ACCLIMATIZATION

- Basically, acclimatization of the material to the expectable required moisture is necessary. For this purpose, the packaging foil will be removed during storage at the place of installation
- If necessary, the changes in lengths have to be considered regarding the design parameters



WALK-ON STABILITY

- Pursuant to the regulations of the german ZVDH (Central Association of German Roofers), under roofs from wood fibres are generally regarded as components not safe to walk on. Load transfer in the area between rafters is therefore not permitted.
- AGEPAN® UDP T+G is safe to tread on in the rafter area. Accident prevention regulations must be observed



DISPOSAL

- Thermal disposal must be restricted in accordance with small heating plants (1.Birmschv)
- Assignment to waste codes 030105, 150103, 170201 (EWC-codes) according to annex 3 of Waste Wood Ordinance



INSTALLATION INSTRUCTIONS

- Tongue points up the ridge/upwards
- The boards must be exactly laid with seamless joints
- The boards are connected with an offset of > 30 cm
- Maximum rafter spacing for 22 mm: 85 cm, for 25 mm: 90 cm, for 32 mm: 100 cm
- Counter-batten fastening depends on the loads
- Fasten the insulation and vapour barrier immediately after laying
- Avoid excessive moisture caused by condensation
- Usable on both sides
- Nail sealing tape is not required
- Continuous top surfaces exceeding approx. 7 m always require an expansion gap**
- Suitable adhesive tapes (e.g. Ampack Ampacoll XT, pro clima® Tescon Vana und Siga Wigluv®) must always be used along with their respective primer.

Please observe the respective manufacturer's instructions



AREAS OF APPLICATION

- External roof and wall sheathing
- Sarking board in compliance with ZVDH regulations for roof pitches $\geq 16^\circ$: UDP-A (in accordance with regular roof pitches)
- Second water-repellent layer in various constructions
- Jamb board can be plastered
- F 60-B (REI 60) constructions in AGEPLAN® SYSTEM
- Areas of application in compliance with DIN 4108-10 table 13: DAD-ds / DEO-ds / WAB-ds / WH

AGEPAN® UDP T+G – DET STABILE UNDERTAG

Kort generel monteringsvejledning



OPBEVARING OG TRANSPORT

- Pladerne skal opbevares vandret og godt understøttet
- Afstanden mellem understøtningerne må ikke overskride 60 cm
- Kanter bør beskyttes mod beskadigelse
- Individuelle plader skal transporteres opretstående, hvis dette er muligt
- Ved udpakning skal den samlede pladetykkelse måles



UDENDØRS EKSPONERING

- Ved brug til undertage er udendørs opbevaring kun muligt i op til otte uger
- Fugtabsorbering ned sætter pladernes styrke, og denne vil ikke kunne genoprettet til fulde, selv efter de er torret
- Midlertidig afdækning af pladerne kan være nyttigt, især hvis der senere skal udføres yderligere arbejde
- Hvis pladerne har absorberet fugt, skal det sikres at de tørres til det påkrævede fugtniveau, før anvendelse
- Husk at tage højde for mulige ændringer af pladelængder i forhold til konstruktionen
- Lodret liggende lægter skal fastgøres ved alle samlinger, og både forsegling og afdækning skal være vind- og vandtætte
- Dræning af overfladevand kan forårsage misfarvning af metaloverflader. Brug derfor passende beskyttelsesfolie, og fjern først dette, når taget er blevet fuldstændigt dækket med plader



AKKLIMATISERING

- Som udgangspunkt er det nødvendigt at akklamatisere pladerne til det forventede påkrævede fugtniveau. Til dette formål skal emballagefolien fjernes under opbevaring på monteringsstedet
- Om nødvendigt skal der tages højde for eventuelle ændringer af pladernes længde ift. konstruktionen



TRÆDESIKKERHED

- I henhold til reglerne fra det tyske ZVDH (Brancheforeningen af Tyske Tagdækker) betragtes dette produkt ikke som et trædesikkert underlag at gå på. Gang mellem spær er derfor ikke tilladt. AGEPLAN® UDP T+G-plader er trædesikre, hvis der er underliggende spær. Forskrifterne til forebyggelse af ulykker skal altid overholdes. Selvom produktet overholder de østrigske ÖNORM 22219-2-gangssikkerhedsstandarder, anbefales det på det kraftigste at udvise forsigtighed.



BORTSKAFFELSE

- Bortskaffelse kan ske til almindelige genbrugsstationer. Pladerne kan afleveres som bændbart materiale
- Klassificeret i henhold til affaldskode 030105, 150103 og 170201 (i Det Europæiske Affaldskatalog) i overensstemmelse med bilag 3 i den tyske forordning om træaffald



MONTERINGSANVISNING

- Feren på en plade skal vende / pege opad (se tegning)
- Pladerne skal monteres præcis med samlinger uden mellemlrum
- Pladerne forbides med en forskydning > 30 cm
- Maksimalt afstand mellem spær med pladetykkelse på 22 mm: 85 cm, med en pladetykkelse på 25 mm: 90 cm, med en pladetykkelse på 32 mm: 100 cm
- Fastgørelsen af lægter afhænger af de givne belastninger
- Isolering og dampspærre - bremse skal opsættes umiddelbart efter montering.
- Undgå overdrevne fugt forårsaget af kondensering.
- Kan anvendes på begge sider.
- Ifølge ZVDH (den tyske brancheforening for tagdækker) er der ikke brug for sombånd.
- Sammenhængende topoverflader, der overstiger en længde på ca. 7 m, kræver en ekspansionsfluge.**
- Anvendt tape (f.eks. Ampack Ampacoll XT, pro clima® Tescon Vana eller Siga Wigluv®) skal altid bruges sammen med den tilhørende grunder.

Følg venligst altid den respektive producents anvisninger.



ANVENDELSESMRÅDER

- Udvendig tag- og vægbeklædning.
- Vindspærre-/undertagsplade i overensstemmelse med ZVDH-regulativerne for taghældninger $\geq 16^\circ$: UDP-A (i henhold til reglerne for almindelige taghældninger).
- Ekstra vandafvisende lag til forskellige konstruktioner.
- Inddækningspladen kan pudses.
- F 60-B (REI 60)-konstruktioner med brug af AGEPLAN® SYSTEM-produkter.
- Anvendelsesområder i henhold til DIN 4108-10, tabel 13:
- DAD-ds / DEO-ds / WAB-ds / WH