

TEBOPIN SELECT



All applications where the natural aesthetic of the wood is important and where the reverse side remains invisible. Joinery works, internal & external fittings, DIY, playgrounds, apparent roof underlays, wall linings, timber framed constructions. High class packing.



Eemporte-piece agency



DESCRIPTION

Base board: Maritime Pine throughout Plywood
Average density (IAW EN 323): 580 kg/m³ (+/- 10%)
Faces (IAW EN 635-3): I / II



Finishing: sanded 2 sides
Bonding (IAW EN 314-2): class 3
Service (IAW EN 636): class 3 exterior conditions
Formaldehyde release classification (IAW EN 13986): E1
Content of Pentachlorophenol (IAW EN 13986): PCP ≈ 0 ppm

SIZES, NUMBER OF PLYS & PACKAGING

Thicknesses (mm)	Number of plies	Sizes (mm)	Packing
7	(3)	2500 x 1250	65
9	(3)		50
10	(5)		45
12	(5)		37
15	(5)		30
18	(7)		25
21	(7)		22
24	(9)		18
25	(9)		18
27	(9)		15
30	(11)		15
35	(13)		13
40	(15)		11
45	(17)		10

Other sizes & thicknesses: on request

OPTIONS

Preservative treatments, fungicide & Insecticide, antitermite: optional on request
 Cutting & TG processing: optional on request

STORAGE

Flat, on intermediate bearers, in an enclosed dry and ventilated building, clear of the ground. As far as storage on site is concerned, provision should be made to cover the panels with an opaque waterproof sheeting with the underside of the stacks clear of the ground.

FURTHER PROCESSING & INSTALLATION

Compliance with standard practice, with regulations and with health and safety rules should be maintained at all times.
 Cutting and machining in the workshop possible except laser technology.

PRODUCTION SITES

Production on Thébault's sites in France



Groupe THEBAULT
 47, rue des Fontenelles - 79 460 MAGNE - France
 Tél : +33 (0)5 49 35 70 20 - Fax : +33 (0)5 49 35 21 10
 info@groupe-thebault.com

www.groupe-thebault.com



TECHNICAL PROPERTIES

Characteristic values (MPa) IAW EN 789 - 1058 for structural calculations IAW Eurocodes

		10	12	15	18	21	25	27	30	35	40
Modulus of elasticity (E _m)	//	8723	7596	9152	9220	8188	6444	7695	7500	7093	6824
	⊥	3727	2078	3298	3230	4262	4815	4755	4950	5357	5626
Bending strength (f _m)	//	20,3	23,2	24,4	23,0	20,4	14,9	18,6	15,5	15,9	16,9
	⊥	17,8	14,8	13,7	12,1	15,1	15,5	14,8	12,7	15,2	15,1
Others characteristic values	Available on DOP Strength in: Tension (f _t), Compression (f _c), Panel shear (f _v) and Planar shear (f _v) Modulus of elasticity in: Tension (E _t), Compression (E _c), Panel shear (G _v) and planar shear (G _v)										

Uses

Use in structural applications (IAW EN 13986, EN 636-3, EN 636-2, EN 636-1)	Suitable for use as structural element in exterior conditions (service class 3), humid conditions (service class 2) and interior conditions (service class 1)
--	---

Bending radius (mm)

Thickness	10	12	15	18
//	2500	3000	3750	4750
⊥	2000	2400	3000	3800

Nail and screw holding (t = 15 mm)

Nail	Face and edge: 30 daN	
Screw	Face	Edge
	180 daN	140 daN

Sound absorption coefficient

IAW EN 13986 Table N°10	Frequency range	
	250 Hz to 500 Hz	1000 Hz to 2000 Hz
	0,10	0,30

Thermal conductivity

IAW EN 13986	λ = 0,13
--------------	----------

Characteristic density

IAW EN 789	540 kg/m ³
------------	-----------------------

Vapour permeability

IAW EN 13986 Table 9	Wet cup	Dry cup
	44 μ	187 μ

Reaction to fire

End use condition In reference to table 8 of EN 13986 - 2004+A1:2015	Minimum thickness	Class excluding floorings	Class floorings
Without an air gap behind the panel	9 mm	D-s2,d0	Dfl-s1
With a closed or an open air gap not more than 22 mm behind the woodbased panel	9 mm	D-s2,d2	-
With a closed air gap behind the wood-based panel	15 mm	D-s2,d1	Dfl-s1
With an open air gap behind the wood-based panel	18 mm	D-s2,d0	Dfl-s1
Any	3 mm	E	Efl

Airborne sound absorption

IAW EN 13986 Paragraph 5.10	The sound transmission loss R of a single wood-based panel, measured in dB, is related the mean surface mass mA en kg/m ² according to the following equation (which is only valid for the frequency range of 1 kHz to 3 kHz and at a surface mass > 5 kg/m ²): R = 13 × lg (mA) + 14
--------------------------------	---

TECHNICAL SUITABILITY & CERTIFICATION

CE Structure attestation of conformity 2+	0380 - DOP* - CPR - EN 13986 : 2004 + A1 : 2015 - EN 636-3 S E1 * DOP : Declaration of Performance available on www.groupe-thebault.com
--	---

Quality marks (country)			Ecocertification	CE Marking	Information on the emission level of volatile substances within the indoor air, showing a risk of toxicity in case of inhalation, based on a scale going from A+ (very low emissions) to C (high emissions). Scenarios flooring/ceiling
NF Extérieur CTB-X (F)	BFU 100 (D)	KOMO (NL)	PEFC™	CE S (Structural)	
	(equivalent) 				